

001945 USA P 03/ETCH/SILICON/JB1
Application No: 09/507,629
Page 2 of 19

IN THE CLAIMS

Please substitute the following listing of claims for the previous listing of claims.

1. (Previously presented) A method of etching a silicon-containing material on a substrate, the method comprising:
placing the substrate in a process chamber; and
providing in the process chamber, an energized gas formed by coupling RF or microwave energy to a process gas comprising fluorine-containing etching gas, chlorine-containing etching gas and sidewall-passivation gas, the sidewall-passivation gas being a gas other than the fluorine-containing etching gas, wherein the volumetric flow ratio of the fluorine-containing etching gas to the chlorine-containing etching gas is from about 2:1 to about 8:1.
2. (Previously presented) A method according to claim 1 wherein the silicon-containing material on the substrate comprises regions having different compositions, and wherein the volumetric flow ratio of the fluorine-containing etching gas, chlorine-containing etching gas, and sidewall-passivation gas is selected to etch the regions having different compositions at substantially similar etch rates.
3. (Original) A method according to claim 2 wherein the silicon-containing material comprises polysilicon.
4. (Original) A method according to claim 3 wherein the regions having different compositions comprise dopant in a plurality of concentrations or types.
5. (Original) A method according to claim 2 wherein the substantially similar etch rates are etch rates that vary by less than about 5%.
6. (canceled)

001945 USA P 03/ETCH/SILICON/JB1
Application No: 09/507,629
Page 3 of 19

7. (Previously presented) A method according to claim 1 wherein the fluorine-containing etching gas comprises one or more of NF_3 , CF_4 or SF_6 .
8. (Previously presented) A method according to claim 1 wherein the chlorine-containing etching gas comprises one or more of Cl_2 or HCl .
9. (Original) A method according to claim 1 wherein the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon-monoxide.
10. (Previously presented) A method according to claim 9 wherein the volumetric flow ratio of the combined volumetric flow rate of the fluorine-containing and chlorine-containing etching gas to the volumetric flow rate of the sidewall-passivation gas is from 1:1 to about 10:1.
11. (Previously presented) A method according to claim 1 wherein the process gas is absent HBr , Br_2 or CH_3Br .
12. (Previously presented) A method according to claim 11 further comprising a second etch step in which an energized gas formed from a second process gas comprising HBr is provided in the process chamber.
13. (Previously presented) A method according to claim 12 wherein the second process gas further comprises one or more of Cl_2 , He-O_2 and CF_4 .

SUBMITTER APPLIED CLAIM 13/14/15 P3/AMEND 000.doc

001945 USA P 03/ETCH/SILICON/JB1
Application No. 09/507,629
Page 4 of 19

14. (Previously presented) A method of etching a substrate in a process chamber while simultaneously cleaning surfaces in the process chamber, the method comprising:

placing the substrate in the process chamber, the substrate comprising a silicon-containing material having a plurality of dopant concentrations or dopant types; and

providing in the process chamber, an energized process gas formed by coupling RF or microwave energy to a process gas comprising fluorine-containing gas, chlorine-containing gas and sidewall-passivation gas, the volumetric flow ratio of the fluorine-containing gas to the chlorine-containing gas being from about 2:1 to about 8:1, whereby the plurality of dopant concentrations or dopant types in the silicon-containing material are etched at substantially similar rates.

15. (Previously presented) A method according to claim 14 wherein the volumetric flow ratio of the fluorine-containing gas, chlorine-containing gas and sidewall-passivation gas, is selected to etch the plurality of dopant concentrations or dopant types in the silicon-containing material at etch rates that vary by less than about 5%.

16. (Canceled)

17. (Original) A method according to claim 14 comprising at least one of the following characteristics (i) the fluorine-containing gas comprises one or more of NF_3 , CF_4 or SF_6 ; (ii) the chlorine-containing gas comprises one or more of Cl_2 or HCl ; or (iii) the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon monoxide.

18. (Previously presented) A method according to claim 14 wherein the volumetric flow ratio of the combined volumetric flow rate of the fluorine containing and chlorine-containing etching gas to the volumetric flow rate of the sidewall-passivation gas is from about 1:1 to about 10:1.

19. (Previously presented) A method according to claim 18 wherein the process gas is absent HBr , Br_2 or CH_3Br .

001945 USA P 03/ETCH/SILICON/JB1
Applicant No. 09/507,829
Page 5 of 19

20. (Previously presented) A method according to claim 19 further comprising a second etch step in which an energized gas formed from a second process gas comprising HBr is provided in the process chamber.

21. (Previously presented) A method according to claim 20 wherein the second process gas further comprises one or more of Cl_2 , He-O_2 and CF_4 .

22. (Withdrawn) A process chamber comprising
a substrate support.
a gas source for providing process gas comprising fluorine-containing gas, chlorine-containing gas, and sidewall-passivation gas,
a gas energizer, and
a gas exhaust,

whereby a substrate received on the support may be processed by process gas provided by the gas source, energized by the gas energizer, and exhausted by the gas exhaust.

23. (Withdrawn) An apparatus according to claim 22 further comprising a controller that is adapted to control the volumetric flow ratio of the fluorine-containing gas, chlorine containing gas, and sidewall-passivation gas to etch regions on the substrate having different compositions at substantially similar etch rates.

24. (Withdrawn) An apparatus according to claim 23 wherein the substantially similar etch rates are etch rates that vary by less than about 5%.

25. (Withdrawn) An apparatus according to claim 24 wherein the volumetric flow ratio of the fluorine-containing gas to the chlorine-containing gas is from about 2:1 to about 8:1.

26. (Withdrawn) An apparatus according to claim 25 wherein the fluorine-containing gas comprises one or more of NF_3 , CF_4 or SF_6 .

SVCLINT-APPLI DCL CHM1945611945 P31AMEND 003.doc

001945 USA P 03/ETCH/SILICON/JB1
Application No: 09/507,629
Page 6 of 19

27. (Withdrawn) An apparatus according to claim 26 wherein the chlorine-containing gas comprises one or more of Cl_2 or HCl .

28. (Withdrawn) An apparatus according to claim 26 wherein the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon monoxide.

29. (Withdrawn) An apparatus according to claim 28 wherein the volumetric flow ratio of the fluorine-containing and chlorine-containing gas to the sidewall-passivation gas is from about 1:1 to about 10:1.

30. (Withdrawn) An apparatus according to claim 26 wherein the controller is adapted not to provide in the process chamber a process gas comprising HBr , Br_2 or CH_3Br .

31. (Withdrawn) An apparatus according to claim 26 wherein the controller is adapted to provide in the process chamber, a second energized gas comprising HBr .

32. (Previously presented) A method of etching a silicon-containing material on a substrate, the method comprising:

placing the substrate in a process chamber;

in a first etching stage, providing in the process chamber, an energized gas formed from a first process gas comprising fluorine-containing etching gas, chlorine-containing etching gas and sidewall-passivation gas, the sidewall-passivation gas being a gas other than the fluorine-containing etching gas, the first process gas being absent HBr , Br_2 or CH_3Br ; and

in a second etching stage, providing in the process chamber, an energized gas formed from a second process gas comprising HBr , Br_2 or CH_3Br .

33. (Previously presented) A method according to claim 32 wherein the silicon-containing material on the substrate comprises regions having different compositions, and wherein the first process gas comprises a volumetric flow ratio of fluorine-containing etching gas, chlorine-containing etching gas and sidewall-passivation gas that is selected to etch the regions having different compositions at substantially similar etch rates.

34. (Original) A method according to claim 33 wherein the silicon-containing material comprises polysilicon.

35. (Original) A method according to claim 33 wherein the regions having different compositions comprise dopant in a plurality of concentrations or types.

36. (Original) A method according to claim 33 wherein the substantially similar etch rates are etch rates that vary by less than about 5%.

37. (Previously presented) A method according to claim 32 wherein the first process gas comprises a volumetric flow ratio of fluorine-containing etching gas to chlorine-containing etching gas that is from about 2:1 to about 8:1.

38. (Previously presented) A method according to claim 32 wherein the fluorine-containing etching gas comprises one or more of NF_3 , CF_4 or SF_6 .

39. (Previously presented) A method according to claim 32 wherein the chlorine-containing etching gas comprises one or more of Cl_2 or HCl .

40. (Original) A method according to claim 32 wherein the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon-monoxide.

41. (Previously presented) A method according to claim 32 wherein the volumetric flow ratio of the combined volumetric flow rate of the fluorine-containing and chlorine-containing etching gas to the volumetric flow rate of the sidewall-passivation gas is from 1:1 to about 10:1.

42. (Previously presented) A method according to claim 32 wherein the second process gas comprises HBr.

43. (Previously presented) A method according to claim 42 wherein the second process gas further comprises one or more of Cl_2 , He-O_2 and CF_4 .

44. (Previously presented) A method of etching a substrate comprising a silicon-containing material having a plurality of dopant concentrations or dopant types, the method comprising:

placing a substrate comprising a silicon-containing material having a plurality of dopant concentrations or dopant types in a process chamber;
in a first etch step, providing in the process chamber an energized gas formed from a first process gas comprising fluorine-containing gas, chlorine-containing gas and sidewall-passivation gas, the volumetric flow ratio of the combined volumetric flow rate of the fluorine-containing and chlorine-containing gas to the volumetric flow rate of the sidewall-passivation gas being from about 1:1 to about 10:1, wherein the volumetric flow ratio is selected such that the plurality of dopant concentrations or dopant types in the silicon-containing material are etched at etch rates that vary by less than about 5%; and
in a second etch step, providing in the process chamber, an energized gas formed from a second process gas comprising HBr.

45. (Previously presented) A method according to claim 44 comprising at least one of the following characteristics (i) the fluorine-containing gas comprises one or more of NF_3 , CF_4 or SF_6 ; (ii) the chlorine-containing gas comprises one or more of Cl_2 or HCl ; or (iii) the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon monoxide.

001945 USA P 03/ETCH/SILICON/JB1
Application No. 09/507,629
Page 9 of 19

46. (Previously presented) A method according to claim 44 wherein the second process gas further comprises one or more of Cl_2 , He-O_2 and CF_4 .

47. (Previously presented) A method of etching a substrate comprising a silicon-containing material having a plurality of dopant concentrations or dopant types, the method comprising:

placing a substrate comprising a silicon-containing material having a plurality of dopant concentrations or dopant types in a process chamber;

in a first etching stage, providing in the process chamber, an energized gas formed from a first process gas consisting essentially of a fluorine-containing gas, a chlorine-containing gas and a sidewall-passivation gas in a volumetric flow ratio selected to etch the plurality of dopant concentrations or dopant types at etch rates that vary by less than about 5%; and

in a second etching stage, providing in the process chamber, an energized gas formed from a second process gas comprising HBr , Br_2 or CH_3Br .

48. (Previously presented) A method according to claim 47 comprising at least one of the following characteristics (i) the fluorine-containing gas comprises one or more of NF_3 , CF_4 or SF_6 ; (ii) the chlorine-containing gas comprises one or more of Cl_2 or HCl ; or (iii) the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon monoxide.

49. (Previously presented) A method according to claim 47 wherein the second process gas further comprises one or more of Cl_2 , He-O_2 and CF_4 .

50. (Currently amended) A substrate etching method comprising:
placing a substrate comprising a silicon-containing material in a process chamber, the silicon-containing material comprising at least one of silicon dioxide, silicon nitride, polysilicon, metal silicide and monocrystalline silicon; and

etching the silicon-containing material by providing in the process chamber, an energized gas formed from a process gas comprising CF_4 , chlorine-containing gas and sidewall-passivation gas.

CLIENT:APPLIED/CLCH/1945/1945 P3/AMEND 003.doc

001945 USA P 03/ETCH/S LICON/JB1
Application No. 09/507,629
Page 10 of 19

51. (Previously presented) A method according to claim 50 wherein the silicon-containing material comprises a plurality of dopant concentrations or dopant types, and wherein the volumetric flow ratio of the CF_4 , chlorine-containing gas, and sidewall-passivation gas is selected to etch the plurality of dopant concentrations or dopant types at etch rates that vary by less than about 5%.

52. (Previously presented) A method according to claim 50 wherein the volumetric flow ratio of the fluorine-containing gas to the chlorine-containing gas is from about 2:1 to about 8:1.

53. (Previously presented) A method according to claim 50 wherein the volumetric flow ratio of the combined volumetric flow rate of the CF_4 and chlorine-containing gas to the volumetric flow rate of the sidewall-passivation gas is from 1:1 to about 10:1.

54. (Previously presented) A method according to claim 50 comprising at least one of the following characteristics (i) the chlorine-containing gas comprises one or more of Cl_2 or HCl , or (ii) the sidewall-passivation gas comprises one or more of nitrogen hydrogen or carbon monoxide.

55. (Previously presented) A method according to claim 50 further comprising a second etch step in which an energized gas formed from a second process gas comprising HBr is provided in the process chamber.

001945 USA P 03/ETCH/SILICON/JB1
Application No. 09/507,629
Page 11 of 19

56. (Currently amended) A substrate etching method comprising:
placing a substrate comprising a silicon-containing material in a process chamber, the silicon-containing material comprising at least one of silicon dioxide, silicon nitride, polysilicon, metal silicide and monocrystalline silicon; and
etching the silicon-containing material by providing in the process chamber, an energized gas formed by coupling RF or microwave energy to a process gas comprising fluorine-containing etching gas, chlorine containing etching gas comprising one or more of Cl_2 and HCl , and sidewall-passivation gas comprising a gas other than the fluorine-containing etching gas.

57. (Previously presented) A method according to claim 56 wherein the silicon-containing material comprises a plurality of dopant concentrations or dopant types, and wherein the volumetric flow ratio of the fluorine-containing etching gas, chlorine-containing etching gas, and sidewall-passivation gas is selected to etch the plurality of dopant concentrations or dopant types at etch rates that vary by less than about 5%.

58. (Previously presented) A method according to claim 56 wherein the volumetric flow ratio of the fluorine-containing etching gas to the chlorine-containing etching gas is from about 2:1 to about 8:1.

59. (Previously presented) A method according to claim 56 wherein the volumetric flow ratio of the combined volumetric flow rate of the fluorine-containing and chlorine-containing etching gas to the volumetric flow rate of the sidewall-passivation gas is from 1:1 to about 10:1.

60. (Previously presented) A method according to claim 56 comprising at least one of the following characteristics (i) the fluorine-containing etching gas comprises one or more of NF_3 , CF_4 or SF_6 ; or (ii) the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon monoxide.

001945 USA P 03/ETCH/SILICON/061
Application No. 09/507,629
Page 12 of 19

61. (Previously presented) A method according to claim 56 further comprising a second etch step in which an energized gas formed from a second process gas comprising HBr is provided in the process chamber.

62. (Currently amended) A substrate etching method comprising:
placing a substrate comprising a silicon-containing material in a process chamber, the silicon-containing material comprising at least one of silicon dioxide, silicon nitride, polysilicon, metal silicide and monocrystalline silicon; and
etching the silicon-containing material by providing in the process chamber, an energized gas formed from a process gas comprising CF₄, Cl₂ and N₂.

63. (Previously presented) A method according to claim 62 wherein the silicon-containing material comprises a plurality of dopant concentrations or dopant types, and wherein the volumetric flow ratio of CF₄, Cl₂ and N₂ is selected to etch the plurality of dopant concentrations or dopant types at etch rates that vary by less than about 5%.

64. (Previously presented) A method according to claim 62 wherein the volumetric flow ratio of CF₄ to Cl₂ is from about 2:1 to about 8:1.

65. (Previously presented) A method according to claim 62 wherein the volumetric flow ratio of the combined volumetric flow rate of CF₄ and Cl₂ to the volumetric flow rate of N₂ is from 1:1 to about 10:1.

66. (Previously presented) A method according to claim 62 further comprising a second etch step in which an energized gas formed from a second process gas comprising HBr is provided in the process chamber.

001945 USA P 03/ETCH/SILICON/JB1
Application No: 09/507,629
Page 13 of 19

67. (Previously presented) A substrate etching method comprising:
placing a substrate comprising a silicon-containing material in a
process chamber; and
etching the silicon-containing material by providing in the process
chamber, an energized gas formed from a process gas consisting essentially of CF_4 , Cl_2
and N_2 .

68. (Previously presented) A method according to claim 67 wherein the
silicon containing material comprises a plurality of dopant concentrations or dopant types
and wherein the volumetric flow ratio of CF_4 , Cl_2 and N_2 is selected to etch the plurality of
dopant concentrations or dopant types at etch rates that vary by less than about 5%.

69. (Previously presented) A method according to claim 67 wherein the
volumetric flow ratio of CF_4 to Cl_2 is from about 2:1 to about 8:1.

70. (Canceled)

71. (Previously presented) A method according to claim 67 further
comprising a second etch step in which an energized gas formed from a second process
gas comprising HBr is provided in the process chamber.

72. (Previously presented) A substrate etching method comprising:
placing the substrate in a process chamber;
in a first etching stage, providing in the process chamber, a first
energized gas formed from a first process gas comprising CF_4 , chlorine-containing gas and
sidewall-passivation gas; and
in a second etching stage, providing in the process chamber, a second
energized gas formed from a second process gas comprising a bromine-containing gas.

73. (Previously presented) A method according to claim 72 wherein the
bromine-containing gas comprises HBr , Br_2 or CH_3Br .

74. (Previously presented) A method according to claim 72 wherein the bromine-containing gas comprises HBr.

75. (Previously presented) A method according to claim 72 comprising at least one of the following characteristics (i) the chlorine-containing gas comprises one or more of Cl_2 or HCl; or (ii) the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon monoxide.

76. (Previously presented) A substrate etching method comprising:
placing the substrate in a process chamber; and
in a first etching stage, providing in the process chamber, a first energized gas formed by coupling RF or microwave energy to a first process gas comprising fluorine-containing etching gas, chlorine-containing etching gas, and sidewall-passivation gas comprising a gas other than the fluorine-containing etching gas; and
in a second etching stage, providing in the process chamber, a second energized gas formed from a second process gas comprising bromine-containing gas.

77. (Previously presented) A method according to claim 76 wherein the bromine-containing gas comprises HBr, Br_2 or CH_3Br .

78. (Previously presented) A method according to claim 76 wherein the chlorine containing etching gas comprises one or more of Cl_2 and HCl.

79. (Previously presented) A method according to claim 78 wherein the bromine-containing gas comprises HBr.

80. (Previously presented) A method according to claim 76 comprising at least one of the following characteristics (i) the fluorine-containing etching gas comprises one or more of NF_3 , CF_4 or SF_6 ; or (ii) the sidewall-passivation gas comprises one or more of nitrogen, hydrogen or carbon monoxide.

001945 USA P 03/ETCH/SILICON/JB1
Application No: 09/507,629
Page 15 of 19

81. (Previously presented) A substrate etching method comprising:
placing the substrate in a process chamber; and
providing in the process chamber, an energized gas formed from a
process gas consisting essentially of CF_4 , Cl_2 and N_2 , wherein the volumetric flow ratio of
the combined volumetric flow rate of CF_4 and Cl_2 to the volumetric flow rate of N_2 is from
about 1:1 to about 10:1.

82. (Previously presented) A method according to claim 81 further
comprising a second etching stage in which an energized gas formed from a second
process gas comprising bromine-containing gas is provided in the chamber.

83. (New) A method according to claim 50 wherein the substrate
comprises a silicon-containing layer consisting essentially of at least one of silicon dioxide,
silicon nitride, polysilicon, metal silicide and monocrystalline silicon, and wherein the
method further comprises etching the silicon-containing layer with the energized gas

84. (New) A method according to claim 56 wherein the substrate
comprises a silicon-containing layer consisting essentially of at least one of silicon dioxide,
silicon nitride, polysilicon, metal silicide and monocrystalline silicon, and wherein the
method further comprises etching the silicon-containing layer with the energized gas

85. (New) A method according to claim 62 wherein the substrate
comprises a silicon-containing layer consisting essentially of at least one of silicon dioxide,
silicon nitride, polysilicon, metal silicide and monocrystalline silicon, and wherein the
method further comprises etching the silicon-containing layer with the energized gas